





# BRIGHT WIRE ROPE - 6 x 36 CLASS

Read important warnings and information in T.O.C. > GENERAL WARNINGS and WIRE ROPE 



6 x 36 WARRINGTON  
SEALE WITH FIBER CORE



6 x 36 WARRINGTON  
SEALE WITH IWRC

According to A.S.T.M. A1023/1023M Wire Rope for General Purposes and Federal Specification RR-W-410, current revision, as applicable. Meets the performance requirements of API-9A. Preformed, right regular lay.

FIBER CORE (EIPS)		
Diameter in Inches	Approx. Weight per foot in Pounds	Breaking Strength in Tons*
1/4	.105	3.01
5/16	.164	4.69
3/8	.236	6.71
7/16	.32	9.1
1/2	.42	11.8
9/16	.53	14.9
5/8	.66	18.4
3/4	.95	26.2
7/8	1.29	35.4
1	1.68	46.0
1.1/8	2.13	57.9
1.1/4	2.63	71.1
1.3/8	3.18	85.5
1.1/2	3.78	101.2

IWRC (EIPS)**		
Diameter in Inches	Approx. Weight per foot in Pounds	Breaking Strength in Tons*
1/4	.116	3.4
5/16	.18	5.27
3/8	.26	7.55
7/16	.35	10.2
1/2	.46	13.3
9/16	.59	16.8
5/8	.72	20.6
3/4	1.04	29.4
7/8	1.42	39.8
1	1.85	51.7
1.1/8	2.34	65.0
1.1/4	2.89	79.9
1.3/8	3.50	96.0
1.1/2	4.16	114.0
1.5/8	4.88	132.0
1.3/4	5.67	153.0
2	7.39	198.0
2.1/4	9.36	247.0
2.1/2	11.6	302.0
2.3/4	14.0	361.0
3	16.6	425.0
3.1/2	22.7	572.0

\*\* EEIPS available in some sizes and constructions.

\*Listed for comparison only. Actual operating loads may vary, but should never exceed the recommended design factor or 20% of catalog Breaking Strength.