




METRIC AND CABLE-LAID WIRE ROPE

Read important warnings and information in T.O.C. > GENERAL WARNINGS and WIRE ROPE 

METRIC WIRE ROPES

6x36 (WS) IWRC, bright, Grade 2160 N/mm² meets the breaking strength requirements of A.S.T.M. A 1023/A 1023M Wire Rope for General Purposes.




6 x 36 WARRINGTON
SEALE WITH IWRC

Diameter in mm	Approx. Weight per Foot in Pounds	Breaking Strength in KN*	Breaking Strength in Tons*
7	.14	37.7	4.24
8	.18	49.2	5.53
9	.23	62.3	7.00
10	.29	76.9	8.64
11	.35	93.0	10.45
12	.41	111.0	12.48
13	.48	130.0	14.61
14	.56	151.0	16.97
15**	.64	170.0	19.11
16	.73	197.0	22.14
18	.93	249.0	27.99
20	1.15	308.0	34.62
22	1.39	372.0	41.81
24	1.65	443.0	49.80

**Not included in A.S.T.M. A 1023/A 1023M

CABLE-LAID WIRE ROPE

Galvanized, preformed TO BE USED FOR MECHANICALLY SWAGED SLINGS ONLY.
Do not use for hand-spliced assemblies or for general purpose operating rope.



7 x 7 x 7
CABLE-LAID



7 x 7 x 19
CABLE-LAID

Diameter Inches	Construction	Metallic Area Square Inch	Approx. Wt. per Foot in Pounds	Breaking Strength in Tons*
3/8	7 x 7 x 7	.062	.22	7.15
1/2	7 x 7 x 7	.099	.37	11.7
5/8	7 x 7 x 7	.159	.6	18.5
3/4	7 x 7 x 19	.217	.81	24.3
7/8	7 x 7 x 19	.281	1.05	31.1
1	7 x 7 x 19	.372	1.38	39.2
1.1/8	7 x 7 x 19	.455	1.72	47.4
1.1/4	7 x 7 x 19	.584	2.18	65
1.1/2	7 x 7 x 19	.794	2.96	88.7

*Listed for comparison only. Actual operating loads may vary, but should never exceed the recommended design factor or 20% of catalog Breaking Strength.