





# STAINLESS STEEL WIRE ROPE

Read important warnings and information in T.O.C. > GENERAL WARNINGS and WIRE ROPE 



6 x 19 (1 + 6 + 12)  
WITH IWRC



6 x 25 FILLER WIRE  
WITH IWRC

## 6 x 19 CLASS STAINLESS STEEL TYPE 304

According to Federal Specification RR-W-410E, preformed, right regular lay, IWRC.  
Some sizes available in Type 316.\*\*

Diameter in Inches	Approx. Wt. per Foot. in Pounds	Breaking Strength in Pounds*/**
7/16	.35	16,300
1/2	.46	22,800
9/16***	.59	28,500
5/8***	.72	35,000
3/4***	1.04	49,600
7/8***	1.42	66,500
1***	1.85	85,400


\*\* Type 316 not covered by Federal Specification RR-W-410E — breaking strength may vary.

\*\*\* Actual construction 6 x 25 (FI)

## 6 x 36 STAINLESS STEEL TYPE 304

According to Federal Specification RR-W-410E\*\*, preformed, right regular lay, IWRC.

Some sizes available in Type 316.\*\*



6 x 36 WARRINGTON  
SEALE WITH IWRC

Diameter in Inches	Approx. Wt. per Foot. in Pounds	Breaking Strength in Pounds*/**
5/16***	.18	8,300
3/8***	.24	11,700
7/16	.35	16,300
1/2	.46	22,800
9/16	.59	28,500
5/8	.72	35,000
3/4	1.04	49,600
7/8	1.42	66,500
1	1.85	85,400
1.1/8	2.34	106,400
1.1/4	2.89	129,400
1.3/8	3.50	153,600
1.1/2	4.16	180,500

\*\* Type 316 not covered by Federal Specification RR-W-410E — breaking strength may vary.

\*\*\* Sizes 5/16" & 3/8" are not covered by RR-W-410E

\*Listed for comparison only. Actual operating loads may vary, but should never exceed the recommended design factor or 20% of catalog Breaking Strength.